



Crescent Bronze Powder Co, Inc.  
3321 County Rd A  
Oshkosh, WI 54901  
p. 800-445-6810  
f. 920-231-8085  
[www.crescentbronze.com](http://www.crescentbronze.com)

## **CRES-LITE® LACQUER PRIMER #10570 PRODUCT INFORMATION**

### **DESCRIPTION**

A durable, fast drying white primer formulated to achieve high adhesion to a variety of substrates, including metal, wood, plaster and certain plastic surfaces. This product dries to a matte finish.

### **APPLICATION**

Dip or spray application strongly advised. Under some circumstances, when working on small surface areas, this product may be brushed, (example: painting small craft items).

### **SURFACE PREPARATION**

The substrate should be completely clean and dry, free of any grease, oil, wax or other contaminants and surface temperature must be at least 50°F. Chromed or plated surfaces must be etched with phosphoric acid or a comparable product to improve primer coat adhesion. Plastic substrates should always be carefully tested to determine the suitability of our product for your intended use. Many plastic substrates, due to the plasticizer content, may appear to accept our product initially, but ultimately may fail a scratch test. Customers working with plastic substrates will need to take the time to do full testing for suitability of the primer to the substrate.

### **TOP COATINGS**

Synthetic Lacquer, Acrylic Lacquer, Low VOC Acrylic Lacquer, Enamel Coatings may be used.

### **DRY TIME**

At 70°F and 50% R.H., dry to touch in 10-20 minutes. May be re-coated in 3-6 hours. Cooler and more humid conditions will extend these timeframes.

### **COVERAGE**

Approximately 300-400 square feet per gallon depending on surface conditions and estimates of overspray, as well as an allowance for any ventilation airflow that may result in loss of material.

### **THINNER/CLEANUP/STORAGE**

Certain spray applications may require a slight (10%) thinning with any aromatic solvent (e.g. xylene or toluene).

### **PHYSICAL DATA**

Weight per gallon:	12.25 lbs.	Flash Point:	<77°F
% Solids by weight:	72.41%	% Pigment by weight	49.0%
weight: V.O.C.:	<406 grams/liter	Viscosity:	85 to 95 K.U

**HAZARDS:**

Please refer to product SDS for suggested guidelines as to the safe use and handling of this product. SDS documents may be obtained from Crescent Bronze via an email request sent to [sds@crescentbronze.us](mailto:sds@crescentbronze.us)

**NOTE: Since we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or accuracy of this information, or the suitability of our products for a given situation. End users of our products should make their own evaluations to determine the suitability of our products for their particular purposes. For this reason, the products discussed here are sold without such warranty, either expressed or implied.**

**Crescent Bronze Powder Co., Inc., is an ISO 9001:2015 registered manufacturer.**

